

Additives, ca. 40 degr C



Base Oils, 40 - 60 degr C



Mixing at 50 - 60 degr C

Blending Tank



Cooling Tank


Bottling

Process Steps:

- Filling
- Heating 0,5 - 2 hours
- Mixing 20 - 40 minutes
- Cooling 1 day

Additives, Room-Temperature

Base Oils, Room-Temperature



Bottling

- Process Steps:**
- **Filling**
 - **Blending xx hour**
 - pre heating to room temperature
 - no cooling